NOTES:

1. SUBSTRATE: Crystal Quartz and MgF2

2. COATING (APPLY ACROSS COATING APERTURE): \$1 & \$2: R(AVG) <0.75% @ 340 - 560nm

DAMAGE THRESHOLD, PULSED: >5 J/cm², 10ns @ 10Hz @ 1064nm

3. SURFACE S1 TO BE PARALLEL TO SURFACE S2 TO WITHIN <10 ARCSEC


4. RETARDANCE: λ/4 ± λ/100 @ 20°C


5. DESIGN WAVELENGTH: 340 - 560 nm

6. TRANSMITTED WAVEFRONT: <λ/4 @ 632nm

7. CONSTRUCTION: Crystalline

8. ROHS: COMPLIANT





FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

Edmund Optics ®

	\$1	\$2	THIRD ANGLE PROJECTION	THIRD ANGLE PROJECTION		12.7mm Dia, 340 - 560nm, λ/4 Achromatic Waveplate	
SURFACE QUALITY	40-20	40-20					
CLEAR APERTURE	> Ø8	>Ø8	ALL DIMS IN	mm	DWG NO	39024	SHEET 1 OF 1